

**COSMO® SL-660.150**

*** COSMOFEN 345 weiß

Adhesive sealant for assembly works**Examples for Application**

- Fast structural bonding of rigid PVC parts
- Plastic window construction Bonding of additional profiles, like sill drips, drain bars, blow bars and shutter bars
- Plastic window construction Bonding of cover caps and shutter guides in PVC profiles
- Plastic window construction: Sealing of profile connections with transom and frame widening during the assembly of the elements
- Construction of trade fair and promotional signs: constructive bonding of integrated rigid foam slab, e.g. FOREX® made of PVC hard
- Bonding of cover/end caps on PVC hard profiles, e.g. fence poles
- Joint sealing up to 7 mm (275.6 mil) joint width , e.g. between window sill and window profile (not suitable for expansion joints e.g. as per DIN EN 15651)

Special Properties

- elastic adhesive joint
- Thixotropic, does not drip off
- Wide range of application possibilities to different plastic materials
- Good weather-proofness
- Good UV-radiation resistance

Certificates / Test reports

French VOC-Emission class C

Technical Data

Basis	Thermoplastic polymers in solvent
Colour hard-dry	white
Viscosity at +20 °C (+68 °F)	medium viscous-pasty
Density as per EN 542 at +20 °C (+68 °F)	approx. 1.01 g/cm ³ (8.43 lb/gal)
Open time at +20 °C (+68 °F), 50 % r.H., application quantity 150 µm (5.9 mil) -glass	approx. 45-60 s
Functional strength for bonding of stress-free battens	approx. 8-10 min
Curing time at +20 °C (+68 °F), 50 % r. H. to ca. 90 %	ca. 24 h
Application quantity for bonding of battens (20 mm (0.79 in) wide)	approx. 8 g/running metre (0.28 oz/running meter)
Application quantity for bonding of battens (40 mm (1.57 in) wide)	approx. 16 g/running metre (0.56 oz/running meter)
Processing temperatures adhesive and substrates	from +10 °C (+50 °F) to +30 °C (+86 °F)

General Information

Diffusion adhesives can only bridge over bonded gaps of <0.2 mm (7.9 mil) in a tensionally locked way.

The here specified time parameters can only be determined accurately by self-tests because they are strongly influenced by material characteristics, temperature, applied quantity, air humidity, material humidity, thickness of adhesive film, press power, and other criterions. Usually, appropriate safety factors are considered for the guiding values.

Industrieverband
Klebstoffe e.V.

Weiss USA LLC
2213 Stafford St Ext., USA Monroe, NC 28111
Telephone: 704 282 4496, <http://www.weiss-usa.com>

made by weiss

**COSMO® SL-660.150**

*** COSMOFEN 345 weiß

Adhesive sealant for assembly works**Preparation**

Acclimatise the product before the application.

The surfaces of the workpieces to be bonded must be dry, and free from dust and grease.

For this purpose we recommend COSMO® CL-300.150.

The cleaning cloths must be lint-free and may not stain.

Bonding

The adhesive is applied on one side of the bonding surfaces as a bead (serpentinous).

Select the adhesive quantity to be applied depending on the material thickness; the adhesive can "penetrate"!

The workpieces must be fit together and pressed within the open time.

After they have been fit together, the parts must be fixed and pressed until functional strength has been reached.

For sealing joints, the mass is applied with an obliquely-cut tip end and then it hardens fully, in this case, the joint is usually not smoothed - it shrinks to approx. 50 % until it is cured.

The bonded joint is loadable after 16 h, the remaining hardening time of the bonded joint can last up to 8 weeks depending on the conditions.

If additional profiles are bonded (bonded surface: PVC-hard) on surfaces with decor film, make sure that the additional profiles rest flat on the window profile. Dose the applied quantity in a way that no adhesive gets out of the bonded joint during bonding.

The so bonded additional profiles may not be exposed to increased temperature/ sun radiation (>+25 °C (>+77 °F)) for about one week. If this is not observed, bubbles can occur in the acryl layer!
Alternatively, a solvent-free system is also available for this application, COSMO® CA-500.130.

Important instructions

Only instructed personnel in specialist firms are allowed to use the product!

KEEP OUT OF REACH OF CHILDREN !

KEEP HOBBOCK, DRUM, CONTAINER, e.g. TIGHTLY CLOSED !

USE ONLY FOR APPLICATIONS MENTIONED IN THE TECHNICAL DATA SHEET !

NO OTHER WARRANTIES EXPRESSED OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. WEISS USA LLC SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES.

Not suitable for bonding pressure tubes!

Our user instructions, processing guidelines, product- and performance data, and other technical statements are only general directives; they describe only the condition of our products (values, determination of values on the date of completion) and the performances do not represent a warranty in the sense of § 443 BGB. **Because of the wide variety of applications of the individual product and the relevant special conditions (e. g. processing parameters, material characteristics, etc.), it is up to the user to test it itself;** our free expert advice for application provided in speech, writing, and as test is nonbinding.

Please, also consider the Safety Data Sheet!

Cleaning

Tools with fresh, not-cured adhesive can be cleaned with COSMO® CL-300.120.

From PVC hard profiles, the cured adhesive is removed after the adhesive has flashed using a scraper and, if necessary, it is further treated with COSMO® CL-300.110.

Storage

Store the hermetically closed original trading units in a dry place at temperatures of +15 °C (+59 °F) to +25 °C (+77 °F) no direct sun radiation.





COSMO® SL-660.150

*** COSMOFEN 345 weiß

Adhesive sealant for assembly works

While transported within the usual transport times, the product may be exposed to temperatures from -30 °C (-22 °F) to +35 °C (+95 °F).

Storage life in unopened original packaging: 24 Months

During the storage time, viscosity is increasing.

Packaging

310 ml (10.48 fl oz) PA cartridge, net weight 305 g (10.8 oz)

Other trading units on request.

