

**COSMO® SP-620.140**

*** COSMOFEN Farbpaste gelb

Paste paint**Examples for Application**

- Dyeing of reaction masses of the product groups COSMO® PU, COSMO® EP and COSMO HD

Special Properties

- Highly concentrated
- No impairment on bonding properties of the dyed adhesive systems provided the specified dosing quantities are met.

Technical Data

Basis	Colouring pigments in paraffin oil
Colour hard-dry	approx. RAL 1028 Melon yellow
Density as per EN 542 at +20 °C	approx. 1.00 g/cm ³
Processing temperatures service product	from +5 °C until +30 °C

Instructions for use

Acclimatise the product before the application.

Before use, agitate/shake it to get a homogeneous substance.

Mix the before mentioned reaction masses in the specified mixing ratio.

Add the paste paint in steps (addition of 0.5 - 1.5 % referred to the reaction mass) until the desired colour has been reached and make it homogeneous.

Important instructions

Only instructed personnel in specialist firms are allowed to use the product!

Our user instructions, processing guidelines, product- and performance data, and other technical statements are only general directives; they describe only the condition of our products (values, determination of values on the date of completion) and the performances do not represent a warranty in the sense of § 443 BGB. **Because of the wide variety of applications of the individual product and the relevant special conditions (e. g. processing parameters, material characteristics, etc.), it is up to the user to test it itself;** our free expert advice for application provided in speech, writing, and as test is nonbinding.

Please, also consider the Safety Data Sheet!

Cleaning

Paste paint can be removed from smooth, non-absorbent substrates using, for instance, COSMO® CL-300.120 und COSMO® CL-300.150.

Residuals on absorbent substrates and work clothing cannot be removed completely anymore.

Storage

Store the hermetically closed original trading units in a dry place at temperatures of +15 °C to +25 °C no direct sun radiation.

While transported within the usual transport times, the product may be exposed to temperatures from -30 °C to +35 °C.

Storage life in unopened original packaging: 12 Months

If the trade units become dented, this can be seen as normal.

Dried-up COSMO® SP-620 paste paints can be re-fluidified with COSMO® CL-300.150.

Packaging

50 ml PE dosing bottle

Other trading units on request.

